

Slip Check to AS 4586-2013
SNOW WHITE, SOLID SURFACE
300x300x12mm THICK

Report Number: M1545

Report Date: 24 March 2023

Total Number of Pages 2

Accredited for compliance with ISO/IEC 17025 – Testing

NATA is a signatory to the ILAC Mutual Recognition Arrangement for the mutual recognition of the equivalence of testing, medical testing, calibration, inspection, proficiency testing scheme providers and reference materials producers reports and certificates

Issued by

Safe Environments Pty Limited
Unit 4, 40 Bessemer Street
Blacktown NSW 2148

Prepared for

Forest One
601 Victoria Street
Abbotsford VIC 3067

Approved by



Nasser Cura
Authorised Signatory

24 March 2023

Test Report No. M1545

Slip Resistance Classification of New Pedestrian Surface Materials

AS 4586-2013 Appendix A (Wet Pendulum Test)

The slip resistance classification has been determined for unused surfaces under specific conditions. Factors such as usage, cleaning systems, applied coatings and patterns of wear may affect the characteristics of the surface after classification. Standards Australia Handbook 198:2014 *Guide to the specification and testing of slip resistance of pedestrian surfaces* provides guidance for the selection of slip resistant pedestrian surfaces classified in accordance with AS 4586-2013. It is recommended that this test report be read in conjunction with AS 4586, HB 197 & HB 198.

Requested by: Forest One
 Client Address: 601 Victoria Street
 Abbotsford VIC 3067
 Product Manufacturer: MEGANITE
 Product Description: SNOW WHITE, SOLID SURFACE 300x300x12mm THICK

Test conducted according to: AS 4586:2013 Appendix A
 Sampling Procedures: Performed by client and tested as received.
 Location: 25/1 Millers Road, Brooklyn 3012
 Conducted by: Billal Emritte

Date: 24 March 2023 Temperature: 19°C
 Sample: Unfixed Cleaning: None
 Rubber slider used: Slider 55 Conditioned: Grade P 400 paper dry followed by wet lapping film
 Slope of specimen: Tested on a flat level surface
 Direction of Test: NA

	Specimen 1	Specimen 2	Specimen 3	Specimen 4	Specimen 5
Mean BPN of last 3 swings:	31	33	33	34	35

Reported SRV of Sample:	33
Temperature Corrected SRV of Sample:	33
Class:	P2

The expanded uncertainty (U_{95}) at the 95% level of confidence with a coverage factor (k) of 2 has been estimated to be 3 BPN or 8 %, whichever is the greater; sampling uncertainty has not been included. The expanded uncertainty should be considered when interpreting results or assessing conformity. Results relate only to items tested.